What is claimed is:

1. An easily adhesive polyamide film that has been stretched in at least one direction and that has been heat treated after coating a separate non-stretched or uniaxially stretched and non-heated polyamide film with a weiter-based coating mixture of which the main components are A, B, and C, whose solid content weight ratio is A/B/C/=98~30/2~70/0.1~10 using a coating amount between 0.005 and 0.030 g/m².

A. Water polyurethane containing acetylene glycol in which two adjacent triple-bonded carbon atoms are replaced with a hydroxyl group and a methyl group, and/or a non-ionic surface active agent which is an addition product of the ethylene oxide

B. A water-soluble polyepoxy compound

C. Particles with an average diameter between 0.001 and 1.0μm

2. An easily adhesive polyamide film as described in Claim 1, containing an surface active agent at a ratio of between 0.01 - 1.0% of the solid content of water polyurethane resin

3. An easily adhesive polyamide film, as described in ~~Claims 1 and 2,~~ coated with between 0.010 and 0.025 g/m² of coating agent

4. A compounded film laminating an easily adhesive coating surface of easily adhesive polyamide film as described in ~~Claims 1, 2 and 3,~~ and other layers